

Ricinash Oil Mill Limited

202/203 Magnum Opus, Shantinagar Industrial Estate,
 Vakola, Santacruz (E), Mumbai – 400055, INDIA
 Tel: +91 22 66963707 | Email: info@ricinash.com
 CIN No. U15140MH1997PLC105499



Product Data Sheet - rev.01/04/19

RiWay-Dx

Oleachemical Derivative

HSN: 2915

Description

RiWay-Dx is a fatty acid ester made from 100% renewable raw materials derived from plant origin. It has versatile properties that allow it to act as: a lubricant, anti-static agent, etc.

Characteristic Values*

Properties	Units	AOCS Test	RiWay-Dx DWX
Physical:		Method	
Appearance	@ 25°C	Visual	White Flakes/Beads
Clarity <small>molten form</small>	Gardner Tube	Visual	Clear
Color (molten)	Gardner Scale	Visual	1+ max.
Moisture	%	Ca 2c-25	1 max.
Melting Point	°C	Cc 1-25	67 +/- 3
Chemical:			
Acid Value	%	Cd 3d-63	3 max.
Saponification Value	mg KOH/g	Cd 3-25	150 – 170
Iodine Value	cg I ₂ /g	Tg 1-64	3 max.

*Slight variations in the characteristic values stated are possible due to production made out of natural raw materials but it shall have no influence on its application functionalities.

Packing: In Bags (net wt. 25 kgs)

Shelf Life / Storage: The shelf life for this material is 12 months from manufacturing date when stored in a cool place (< 40°C), in tightly closed packaging, protected from dust, heat, & moisture.

Applications

Industry: Plastics	Function	Benefits	Dosage %
PVC	External Lubricant	Mold Release	0.3 – 1.0
PP, PE	Anti-Static	Reduces Static Charge, Minimizes Dust Pick-up	0.3 – 1.0
EPS	External Lubricant Anti-Static	Mold-Release Reduces Static Charge, Minimizes Dust Pick-up	0.3 – 1.0
SAN, PA	Internal Lubricant	Reduces Melt Viscosity, Gives Thermal Stability, Better Optical Properties	0.3 – 1.0

Authorization: (sign not necessary if emailed doc.)

Prepared by:	Approved by:	Released by:
EX – TECH	EX – MFNG	EX - MKTG

The information and statements herein are believed to be reliable but are not to be construed as a warranty or representation for which we assume legal responsibility. Users should undertake enough verification and testing to determine the suitability for their own particular purpose of any information or products referred to herein. NO WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE IS MADE. Nothing herein is to be taken as permission, inducement or recommendation to practice any patented invention without a license.