

RiWay-Lx

Oleochemical Derivative

HSN: 29161590

Description

RiWay-Lx is a fatty acid ester made from 100% renewable raw materials derived from plant origin. It has versatile properties that allow it to act as: a lubricant, antifogging agent, etc.

Characteristic Values*

Properties	Units	AOCS Test Method	RiWay-Lx GMO
Physical:			
Appearance	@ 25°C	Visual	Lt. Yellow Liquid
Clarity <small>molten form</small>	Gardner Tube	Visual	Clear
Color <small>molten form</small>	Gardner Scale	Visual	2 max
Moisture	%	Ca 2c-25	1 max
Viscosity <small>bubble secs</small>	@ 25°C Gardner Tube	Tq 1a-64	6 - 9
Chemical:			
Acid Value	mg KOH/g	Cd 3d-63	2 max
Saponification Value	mg KOH/g	Cd 3-25	150 – 170
Iodine Value	cg I ₂ /g	Tg 1-64	65 – 85
Hydroxyl Value	mg KOH/g	Cd 13-60	300 – 330
Monoglycerides.	%	Cd 11b-91 (GC)	35 min
Free Glycerol	%	Cd 11b-91 (GC)	5 max
Soap as K Stearate	%	RRMPL	0.3 max

*Slight variations in the characteristic values stated are possible due to production made out of natural raw materials but it shall have no influence on its application functionalities.

Packing: In Plastic Barrels (net wt. 200 kgs)

Shelf Life / Storage: Shelf life is 12 months from manufacturing date when stored in a cool place (< 35°C), in tightly closed packaging, protected from dust, heat, & moisture.

Applications

Industry: Plastics	Key Role	Benefits	Dosage %
PVC	Internal Lubricant Anti-Fog	Reduces Melt Viscosity, Gives Thermal Stability, Better Optical Properties Retards Fogging on Films & Yields Transparency	0.3 – 1.0
PE	Anti-Fog	Retards Fogging on Films & Yields Transparency	0.3 – 1.0

Authorization: (sign not necessary if emailed doc.)

Approved by:	Approved by:	Approved by:
TECH: EX	MFGN: EX	MKTG: EX

The information contained in this document is based on our own research and development and is to the best of our knowledge reliable. Users should, however, conduct their own tests to determine the suitability of our products for their own specific purposes and the legal status for their intended use of the product. Statements contained herein should not be considered as a warranty of any kind, expressed or implied, and no liability is accepted for the infringement of any patents.